



**No. 1299109.7**

(Please quote this number in all correspondence)

CLIENT:  
Floorco Trading Ltd.  
38 Galway St.  
Onehunga, Auckland

SAMPLE RECEIVED FROM:  
Floorco

Date Received: 1.9.19

SAMPLE DESCRIPTION:  
SPC Vinyl Flooring.

Attn.: Henry Zhai

Client Order No.:

Client Reference: **Interim Report**

1 of 2

## ISO 20251:2016(E) – TEXTILE FLOOR COVERINGS – WATER IMPERMEABILITY TEST

PVC Open-ended Cylinder Used: 100mm diameter (modified)  
Samples tested in conditioned state (20°C, 65% RH)

	Middle Area	Joint Area
Results:	Water Impermeability	Water Impermeability

## AS 4586-2013 – SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS Appendix A: Wet Pendulum Test Method

Test Temperature: 22°C  
Sample Preparation: Washed with pH neutral detergent and dried.  
Test Direction: Length  
Fixed/Unfixed: Unfixed  
Slider Used: Slider 96, Batch No. 87  
Equipment: Cooper Pendulum Skid Tester Serial No. 1433-01  
Slider prepared using P400 and 3µm lapping film.

Length:	1	2	3	4	5	SRV (Slip Resistance Value)
British Pendulum Number:	40	38	40	38	38	39

**Classification: P3**

**Table 2: Classification of Pedestrian Surface Materials According to the AS 4586 Wet Pendulum Test**

Class	Pendulum SRV (see note)	
	Slider 96	Slider 55
P5	>54	>44
P4	45-54	40-44
P3	35-44	35-39
P2	25-34	20-34
P1	12-24	<20
P0	<12	


Note: While Slider 96 or Slider 55 rubbers may be used, the test report shall specify the rubber that was used.

**Slip Resistance (Dry) results to follow.**

### "THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

L A Greer  
Signatory

  
C Judan  
Signatory

01/11/2019

**New Zealand Wool Testing Authority Ltd**

22 Bridge Street, PO Box 12065

Ahuriri, Napier 4144, New Zealand

T +64 6 835 1086, F +64 6 835 6473 Email: testing@nzwta.co.nz



# NZWTA

**No. 1299109.7**

(Please quote this number in all correspondence)

**CLIENT:**  
Floorco Trading Ltd.  
38 Galway St.  
Onehunga, Auckland

**SAMPLE RECEIVED FROM:**  
Floorco

**Date Received:** 1.9.19

**Attn.:** Henry Zhai

**SAMPLE DESCRIPTION:**  
SPC Vinyl Flooring.

**Client Order No.:**

**Client Reference:** Interim Report


2 of 2



**"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

L A Greer  
Signatory

  
C Judan  
Signatory

01/11/2019

**New Zealand Wool Testing Authority Ltd**

22 Bridge Street, PO Box 12065

Ahuriri, Napier 4144, New Zealand

T +64 6 835 1036, F +64 6 835 6473 Email: testing@nzwta.co.nz