

**No. 1487242.8**

(Please quote this number in all correspondence)

CLIENT:  
Floorco Trading Ltd.  
38 Galway St.  
Onehunga, Auckland

SAMPLE RECEIVED FROM:  
Floorco

Date Received: 31.10.23

Attn.: Terry Shi

SAMPLE DESCRIPTION:  
Flooring Planks – VSPC Woodface 8mm.

Client Order No.:

Client Reference:

1 of 3

**AS 4586-2013 – SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS  
Appendix A – Wet Pendulum Test Method**

**Note:** This test was sub-contracted (Test Number 23-004573).

Test Temperature: 22°C  
Sample Preparation: Washed with pH neutral detergent and dried.  
Test Direction: Length  
Fixed/Unfixed: Unfixed  
Slider Used: Slider No. 96, Batch No. 23  
Equipment: Cooper Pendulum Skid Tester Serial No. 1433-01  
Slider prepared using P400 and 3µm lapping film.

Length:	1	2	3	4	5	SRV (Slip Resistance Value)
British Pendulum Number:	37	40	41	40	42	40

**Classification: P3**


**Table 2: Classification of Pedestrian Surface Materials According to the AS 4586 Wet Pendulum Test**

Class	Pendulum SRV	
	Slider 96	Slider 55
P5	>54	>44
P4	45-54	40-44
P3	35-44	35-39
P2	25-34	20-34
P1	12-24	<20
P0	<12	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

**“THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED”**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.



C Judan  
Key Technical Person

12/12/2023

**No. 1487242.8**

(Please quote this number in all correspondence)

CLIENT:  
Floorco Trading Ltd.  
38 Galway St.  
Onehunga, Auckland

SAMPLE RECEIVED FROM:  
Floorco

Date Received: 31.10.23

Attn.: Terry Shi

SAMPLE DESCRIPTION:  
Flooring Planks – VSPC Woodface 8mm.

Client Order No.:

Client Reference:

2 of 3

**AS 4586-2013 – SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS  
Appendix B – Dry Floor Friction Test Method**

**Note:** This test was sub-contracted (Test Number 23-004573).

Air Temperature: 21°C  
 Sample Preparation: Washed with pH neutral detergent, rinsed then dried.  
 Sample & Test Direction: Sampling conducted by client. Test direction parallel with embossed grain.  
 Fixed/Unfixed: Unfixed  
 Slider Rubber: Slider 96, Batch No. 20 Prepared on P400 Sic Paper.  
 Test Equipment: Tortus Floor Friction Tester, Tortus Model MK II Serial No. 318

	Run 1	Run 2	Mean (rounded to 0.05)
Dynamic Coefficient Friction:	0.65	0.60	0.65

**Classification: D1**


**Table 3: Classification of Pedestrian Surface Materials According Dry Floor Friction Test**

Classification	Floor Friction Tester Mean Value
D1	≥0.40
D0	<0.40

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

**“THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED”**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.



C Judan  
Key Technical Person

12/12/2023

**No. 1487242.8**

(Please quote this number in all correspondence)

CLIENT:  
Floorco Trading Ltd.  
38 Galway St.  
Onehunga, Auckland

Attn.: Terry Shi


Client Order No.:

SAMPLE RECEIVED FROM:  
FloorcoSAMPLE DESCRIPTION:  
Flooring Planks – VSPC Woodface 8mm.

Client Reference:

Date Received: 31.10.23

3 of 3

**"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

  
C Judan  
Key Technical Person

12/12/2023